

## Scandium-Substituted $\text{Na}_3\text{Zr}_2(\text{SiO}_4)_2(\text{PO}_4)$ as Superior Sodium-Ion Conductors

Frank Tietz, Qianli Ma, Marie Guin, Sahir Naqash, Chih-Long Tsai, Olivier Guillon

<sup>1</sup> Institute of Energy and Climate Research – IEK-1, Forschungszentrum Jülich GmbH, 52425 Jülich, Germany; <sup>2</sup> Jülich Aachen Research Alliance, Section JARA-Energy, 52425 Jülich, Germany <sup>3</sup> Helmholtz-Institute Münster – Ionics in Energy Storage, Forschungszentrum Jülich GmbH, Corrensstraße 46, 48149 Münster, Germany;

E-Mail: [f.tietz@fz-juelich.de](mailto:f.tietz@fz-juelich.de)

Room-temperature Na-ion batteries (NIBs) show advantages of unlimited sources, low price of starting materials and easy recycling [1], which make them promising candidates for stationary energy storage applications. NIBs in all-solid-state design are regarded as the batteries of the next generation due to their non-leaking, non-volatile, non-flammable electrolyte and adaptability to temperature changes [2]. Trivalent cation-substituted  $\text{Na}_3\text{Zr}_2(\text{SiO}_4)_2(\text{PO}_4)_3$  in NASICON structure are regarded as promising electrolyte materials for solid-state or high-temperature batteries because of their high  $\text{Na}^+$  ion conductivity and reliable chemical and physical stability. In this study, scandium has been chosen as the substitution element in the solid solution  $\text{Na}_{3+x+y}\text{Sc}_x\text{Zr}_{2-x}(\text{SiO}_4)_y(\text{PO}_4)_{3-y}$  (NSZSP), because among all the trivalent cations, the ionic radius of  $\text{Sc}^{3+}$  (74.5 pm) is the closest to that of  $\text{Zr}^{4+}$  (72.0 pm), indicating that the substitution only generates a deficiency in positive charge, but does not cause distortions in the crystal structure. NSZSP has received hardly any attention so far and only few reports are available on this kind of materials [3, 4]. However, in the past the performance of NSZSP was compared at high temperatures ( $\approx 300^\circ\text{C}$ ). Only a few conductivities at room temperature were mentioned, and they were rather moderate (maximum  $5.0 \cdot 10^{-4} \text{ S} \cdot \text{cm}^{-1}$ ). In this study, a solution-assisted solid-state reaction method was applied by which a series of NSZSP nano-powders with favorable microstructures were prepared. With increasing scandium substitution, the conductivity of sintered NSZSP samples also increases.  $\text{Na}_{3.4}\text{Sc}_{0.4}\text{Zr}_{1.6}(\text{SiO}_4)_2(\text{PO}_4)$  shows the highest conductivity of the system. Higher amounts of scandium decrease the conductivity due to the decreasing number of available vacancies for  $\text{Na}^+$  ion transport. The total ionic conductivity of  $\text{Na}_{3.4}\text{Sc}_{0.4}\text{Zr}_{1.6}(\text{SiO}_4)_2(\text{PO}_4)$  reaches  $4.0 \cdot 10^{-3} \text{ S} \cdot \text{cm}^{-1}$  at  $25^\circ\text{C}$  [5]. To our knowledge, it is not only the best value for all materials with NASICON-type structure, but also the best reported value for all polycrystalline oxidic  $\text{Na}^+$  ion conductors. It is even comparable with common liquid electrolytes of NIBs.

- [1] Towards Greener and more Sustainable Batteries for Electrical Energy Storage, D. Larcher, J. M. Tarascon, *Nature Chem.* 7 (2015) 19.
- [2] Superionic Glass-ceramic Electrolytes for Room-temperature Rechargeable Sodium Batteries, A. Hayashi, K. Noi, A. Sakuda, M. Tatsumisago, *Nature Commun.* 3 (2012) 856.
- [3] The Preparation, Structure, and Conductivity of Scandium-substituted NASICONs, M. A. Subramanian, P. R. Rudolf, A. Clearfield, *J. Solid State Chem.* 60 (1985) 172.
- [4] Sodium and Oxygen Disorder in a Scandium-substituted Nasicon: A Time of Flight Neutron Powder Diffraction Study of  $\text{Na}_{2.5}\text{Zr}_{1.8}\text{Sc}_{0.2}\text{Si}_{1.3}\text{P}_{1.7}\text{O}_{12}$ , P. J. Squattrito, P. R. Rudolf, P. C. Hinson, A. Clearfield, K. Volin, J. Jorgensen, *Solid State Ion.* 31 (1988) 31.
- [5] Scandium-substituted  $\text{Na}_3\text{Zr}_2(\text{SiO}_4)_2(\text{PO}_4)$  Prepared by a Solution-assisted Solid-state Reaction Method as Sodium-ion Conductors, Q. Ma, M. Guin, S. Naqash, C.-L. Tsai, F. Tietz, O. Guillon, *Chem. Mater.* 28 (2016) 4821.

