

## Making the Most of Neutron-Diffraction Data Lithium Diffusion Pathways in Ramsdellite-Like $\text{Li}_2\text{Ti}_3\text{O}_7$

Dennis Wiedemann<sup>1</sup>, Alexandra Franz<sup>2</sup>

<sup>1</sup> Institut für Chemie, Technische Universität Berlin, Straße des 17. Juni 135, 10623 Berlin, Germany; <sup>2</sup> Abteilung Struktur und Dynamik von Energiematerialien, Helmholtz Zentrum Berlin, Hahn-Meitner-Platz 11, 4109 Berlin, Germany

E-Mail: [dennis.wiedemann@chem.tu-berlin.de](mailto:dennis.wiedemann@chem.tu-berlin.de)

Ramsdellite-like  $\text{Li}_2\text{Ti}_3\text{O}_7$  exhibits fast and strongly anisotropic lithium-ion conduction. Although proposed applications range from energy storage to lithium processing, the crucial diffusion pathways in this material have not yet been studied in depth; even aspects of its crystal structure are still under discussion [1].

In our studies, we have examined  $\text{Li}_2\text{Ti}_3\text{O}_7$  using variable-temperature neutron diffraction to probe its nontrivial lithium-ion distribution. At 24 °C, a Rietveld-refined structural model with anharmonic-anisotropic displacement parameters shows a statically disordered snapshot of the dynamic behavior during synthesis. We found no significant occupation of the framework cation positions by lithium ions and agree with the recently favored formulation as  $[\text{Li}_{2\Box_5}]_i[(\text{Ti}_{3\Box_{0.5}})\text{O}_7]_f$  ( $\Box$ : vacancy, i: interstitial, f: framework). Reconstruction of the scattering-length density via maximum-entropy methods (MEM) indicates successive partial relaxation and activation of lithium movement with increasing temperature in the metastability range.

Using topological analyses of procrystal voids and Voronoi-Dirichlet partitioning (VDP), we have identified two pathways of lithium diffusion: interstitial migration along ribbons as the major, framework migration through vacancies as the most probable minor mechanism. Thusly, we explain former empirical results and shed light on this paradigmatic lithium-ion conductor [2].




Figure 1: Void structure of the  $\text{Ti}_3\text{O}_7^{2-}$  framework at 422 °C (gray: titanium, red: oxide ions, blue: preferred, green: probabilistic voids/channels).

- [1] Pseudo-weak-phase-object Approximation in High-resolution Electron Microscopy. II. Feasibility of Directly Observing  $\text{Li}^+$ , D. Tang, C. M. Teng, J. Zou, F. H. Li, Acta Cryst. B 42 (1986) 340.
- [2] Lithium Diffusion Pathways in Metastable Ramsdellite-like  $\text{Li}_2\text{Ti}_3\text{O}_7$  from High-temperature Neutron Diffraction, D. Wiedemann, S. Nakhil, A. Franz, M. Lerch, Solid State Ion. 293 (2016) 37.