

# ***In-operando* Electron Paramagnetic Resonance Spectroscopy of Lithium Anodes During Electrochemical Cycling**

P. Jakes,<sup>1</sup> J. Wandt,<sup>2</sup> C. Marino,<sup>2</sup> H. A. Gasteiger,<sup>2</sup> R.-A. Eichel,<sup>1,3</sup> J. Granwehr<sup>1</sup>

<sup>1</sup>Institut für Energie- und Klimaforschung (IEK-9), Forschungszentrum Jülich

<sup>2</sup>Technical Elektrochemistry, Technische Universität München, Garching

<sup>3</sup>RWTH Aachen University, Institute of Physical Chemistry, Aachen

Corresponding author: Peter Jakes, E-Mail: [p.jakes@fz-juelich.de](mailto:p.jakes@fz-juelich.de)

The formation of mossy lithium and lithium dendrites so far prevents the use of lithium metal anodes in lithium ion batteries. *In-operando* measurement techniques to monitor mossy lithium and dendrite formation during electrochemical cycling can help to develop solutions for this problem [1].

*In-operando* conduction electron paramagnetic resonance (EPR) spectroscopy [2] is presented as a modality for time-resolved monitoring of lithium plating/dissolution mechanisms in a lithium-metal/LiFePO<sub>4</sub> (LFP) cell. The experiments are made possible by a novel concentric battery cell design that is compatible with resonators used in standard EPR spectrometers operating in the X band frequency range. It is shown that the time-resolved *in-operando* EPR data are consistent with *post mortem* scanning electron microscopy (SEM) analysis.

To demonstrate the viability of the *in-operando* EPR method, two cells using different electrolytes were studied. When using an electrolyte containing fluoroethylene carbonate (FEC) additive [3], a higher reversibility of the lithium anode and a reduced formation of mossy lithium were observed.

Experimental support by Hans Kungl, Magnus Graf, Johannes Landesfeind and Yi-Chun Lu as well as financial support by BMW AG, by the Bavarian Ministry of Economic Affairs and Media, Energy and Technology (EEBatt project; TUM) and by the German Federal Ministry of Education and Research (BMBF-project DESIREE, grant number 03SF0477A; IEK-9) are gratefully acknowledged.

## **References**

- [1] R. Bhattacharyya, B. Key, H. Chen, A. S. Best, A. F. Hollenkamp, and C. P. Grey, "In situ NMR observation of the formation of metallic lithium microstructures in lithium batteries.," *Nat. Mater.*, **9**, 504–510 (2010).
- [2] G. Feher, A. F. Kip, "Electron Spin Resonance Absorption in Metals. I. Experimental," *Phys. Rev.*, **98**, 337–348 (1955).
- [3] R. McMillan, H. Slegel, Z.X. Shu, and W.D. Wang, "Fluoroethylene carbonate electrolyte and its use in lithium ion batteries with graphite anodes," *J. Power Sources*, **81–82**, 20–26 (1999).

